

# Stripper L 10

Stripper L 10 is an acidic process for chemical stripping of nickel, tin respectively combined layer systems of tin and nickel from base materials like copper, brass as well as to a limited extend from German silver (e.g. 2.0740). The base metal is only attacked marginally so it can be usually re-plated without any losses of quality.

The information in this data sheet is based on laboratory as well as practical experience. Figures quoted for operating limits and replenishment quantities are for guidance. Actual values necessary will depend on the components being plated (material and geometry), their application and plating plant conditions.

## Important:

Please read this instruction carefully prior to the use of the process and carefully follow all the parameters that have a direct influence on the operation. We reserve the right to make technical changes. In the interest of safety, please pay attention to the hazard warnings on the labels of the containers. The minimum shelf life of the products is included on the labels and is also available in the appropriate Quality Assurance (QA03).

The current IMDS number of the layer deposited from the process is available on the internet at [www.schloetter.com/downloads](http://www.schloetter.com/downloads).

For the storage of chemical products the TRGS 510 must be followed.

