

Bright Chrome

SLOTOCHROM DC 150

Bright Chrome DC 150 is an easy to operate chrome electrolyte with a very variable chromic acid content. Trouble-free deposition is possible with a chromic acid content of only 150 g/l. If desired a 300 g/l chromic acid content may be used without any problems.

The concentration of chromic acid as well as the respective additives are maintained with Compound DC 150. The components of the electrolyte can be easily monitored analytically.

In general, it's possible to convert conventional chrome electrolytes to Bright Chrome SLOTOCHROM DC 150.

The information in this data sheet is based on laboratory as well as practical experience. Figures quoted for operating limits and replenishment quantities are for guidance. Actual values necessary will depend on the components being plated (material and geometry), their application and plating plant conditions.

Important:

Please read these instructions carefully and follow recommendations given. We reserve the right to make technical changes as necessary. In the interests of safety, please pay attention to the R- and S- phrases on the labels of the containers. The minimum shelf life of the additives is printed on the label of the container. The current IMDS number of the layer deposited from the process can be found on the internet at www.schloetter.com/downloads.

For the storage of chemical products only the TRGS 514 and TRGS 515 regulations must be followed. The Hazardous Goods Regulation (ADR/GGVS) are only valid **for transportation** and must not be applied to storage.

